

## **Reference Material Certificate**

# 822/01

Aluminium Base (Type of Standard) AlZn(Si), Set 820

## **Certified Values**

Element	Mass content [%]	Uncertainty [%]
Silicon (Si)	(0.08)	
Iron (Fe)	(0.09)	
Copper (Cu)	0.004	
Manganese (Mn)	0.007	
Magnesium (Mg)	0.008	
Chromium (Cr)	0.009	
Nickel (Ni)	0.006	
Zinc (Zn)	0.008	
Titanium (Ti)	0.06	
Bismuth (Bi)	0.043	
Tin (Sn)	0.10	
Vanadium (V)	0.011	

Values in brackets ( ) are not certified but given for information only.

#### Manufacturing

This standard is produced using six strand hot top vertical continuous casting out of single melt.

#### Homogeneity

Homogeneity testing is performed by means of spark emission spectroscopy. Tests involve making multiple measurements on individual samples taken at regular intervals along the entire length of each cast rod. Depending on the mass content of the element, the relative standard deviation of multiple measurements between discs or within one disc is typically found between 0.3% - 1% for alloying and other elements and 0.5% - 5% for trace elements.

#### **Analysis**

The values listed in this analysis certificate are the results of multiple analyses performed in our chemical analysis laboratory. The analyses are based on established wet chemical procedures.

### **Description of Sample**

This reference material is available in the form of discs (approx. Ø 60 x 25 mm).

#### Intended use and Stability

This certified reference material is primarily intended for use in spark optical emission spectroscopy. Other applications are X-ray fluorescence spectrometry (XRF) and classical wet chemical procedures. The minimum sample size for wet chemical analysis is 0.2g. The material will remain stable for the period given below (certification validity) if it is stored in a dry and clean environment at room temperature.

#### **Instructions for Use**

Calibration measurements should be made within a ring between 2mm and 22mm from the edge of the CRM face. For wet chemical analysis chips have to be prepared by turning or milling of the sample surface.

## **Traceability**

Traceability of the certified mass contents to the SI (Système International d'Unités) is ensured by calibration using certified standard solutions or pure metals or substances of known stoichiometry.

Dr. Benedikt Moser CTO

Suisse Technology Partners Ltd. Querstrasse 5 8212 Neuhausen am Rheinfall Switzerland

Phone: +41 52 551 11 00 Fax: +41 52 551 11 99 Email: refmat@suisse-tp.ch

Internet: https://reference-materials.ch

Date of certification: 1991

Certificate version 002: 31-Mar-2020 This certificate is valid until: Dec-2066

Patrik Bachmann Head of Inorganic Analytics

Badlemen

White area to

be used for

analysis.

20 mm

= 2 mm