

## Reference Material Certificate

# 525/04

Aluminium Base (Type of Standard)  
AlMg, Set 520

### Certified Values

Element	Mass content [%]	Uncertainty [%]
Silicon (Si)	0.220	± 0.006
Iron (Fe)	0.313	± 0.007
Copper (Cu)	0.066	± 0.002
Manganese (Mn)	0.285	± 0.007
Magnesium (Mg)	2.87	± 0.06
Chromium (Cr)	0.327	± 0.010
Nickel (Ni)	0.028	± 0.001
Zinc (Zn)	0.035	± 0.002
Titanium (Ti)	0.029	± 0.001
Beryllium (Be)	0.00053	± 0.00005
Bismuth (Bi)	0.024	± 0.002
Calcium (Ca)	0.0007	± 0.0002
Cadmium (Cd)	0.0008	± 0.0001
Gallium (Ga)	0.021	± 0.001
Lithium (Li)	0.0015	± 0.0002
Sodium (Na)	0.0013	± 0.0002
Lead (Pb)	0.021	± 0.002
Antimony (Sb)	0.004	± 0.001
Tin (Sn)	0.016	± 0.002
Vanadium (V)	0.018	± 0.001
Zirconium (Zr)	0.0058	± 0.0003

The uncertainty reported is the result of standard deviation of all results multiplied with a factor of two and represents approximately the 95% confidence interval.

## Manufacturing

This standard is produced using melt spinning, chopping and mixing followed by hot pressing and extrusion.

## Homogeneity

Homogeneity testing is performed by means of spark emission spectroscopy. Tests involve making multiple measurements on individual samples taken at regular intervals along the entire length of each cast rod. Depending on the mass content of the element, the relative standard deviation of multiple measurements between discs or within one disc is typically found between 0.3% - 1% for alloying and other elements and 0.5% - 5% for trace elements.

## Analysis

The values listed in this analysis certificate are the results of multiple analyses performed in our chemical analysis laboratory which is an accredited test facility for aluminium alloys according to the international standard ISO 17025. The analyses are based on established wet chemical procedures.

## Description of Sample


This reference material is available in the form of discs (approx. Ø 65 x 24 mm).

## Intended use and Stability

This certified reference material is primarily intended for use in spark optical emission spectroscopy. Other applications are X-ray fluorescence spectrometry (XRF) and classical wet chemical procedures. The minimum sample size for wet chemical analysis is 0.2g. The material will remain stable for the period given below (certification validity) if it is stored in a dry and clean environment at room temperature.

## Instructions for Use

Calibration measurements should be made within a ring between 2mm and 22mm from the edge of the CRM face. For wet chemical analysis chips have to be prepared by turning or milling of the sample surface.



## Traceability

Traceability of the certified mass contents to the SI (Système International d'Unités) is ensured by calibration using certified standard solutions or pure metals or substances of known stoichiometry.

Dr. Benedikt Moser  
CTO

Patrik Bachmann  
Head of Inorganic Analytics

Suisse Technology Partners Ltd.  
Querstrasse 5  
8212 Neuhausen am Rheinfall  
Switzerland

Phone: +41 52 551 11 00  
Fax : +41 52 551 11 99  
Email: [refmat@suisse-tp.ch](mailto:refmat@suisse-tp.ch)  
Internet: <https://reference-materials.ch>

Date of certification: 21-May-2013  
Certificate version 003: 04-Jan-2022  
This certificate is valid until: May-2088